

HEAVY LAYERS OF MASS

High-density viscoelastic sheets (1230×1030 mm) in 5 or 10 kg/m². Increase surface mass to improve sound isolation in demanding technical applications.



The **AKUSTIKABSORBER HEAVY LAYERS** range consists of **high-density viscoelastic sheets** designed to **improve airborne sound isolation by increasing the surface mass** of walls, panels and enclosures. Flexible and easy to adapt, they can be used as **acoustic barriers** or incorporated as an **intermediate layer in multilayer systems**.

Manufactured from a **highly mineral-filled viscoelastic material**, they are available in two standard surface masses: **5 kg/m² and 10 kg/m²**, allowing the acoustic performance to be adapted to the requirements of each application. Their viscoelastic behaviour also provides an additional **damping effect**, helping to reduce panel vibration and resonance.

HEAVY LAYERS are supplied in **1230 × 1030 mm sheets**, making them easy to cut and adapt to **machinery enclosures, equipment housings, panels, floors and technical compartments**. Their high surface mass makes them particularly effective for **improving sound isolation, especially at low frequencies**, and enhancing the overall performance of multilayer acoustic systems.



AMC MECANOCAUCHO
Industrialdea Zona A - Pab. 35.
Asteasu E-20159, Gipuzkoa
Spain



Tel.: +34 843 74 00 13



sales@amcsa.es



www.mecanocaucho.com

Drawings

MP5 A

Type	Code	Self-adhesive	Density(kg/m ³)	Weight/m2 (kg)	Thickness(mm)
MP5 A	26603	1-Side	1950	5	2.6

MP10 A

Type	Code	Self-adhesive	Density(kg/m ³)	Weight/m2 (kg)	Thickness(mm)
MP10 A	26604	✓ 1-Side	1950	10	5

MP5 AA

Type	Code	Self-adhesive	Density(kg/m ³)	Weight/m2 (kg)	Thickness(mm)
MP5 AA	26605	✓ 2-Side	1950	5	2.6

MP10 AA

Type	Code	Self-adhesive	Density(kg/m ³)	Weight/m2 (kg)	Thickness(mm)
MP10 AA	26606	✓ 2-Side	1950	10	5





AMC MECANOCAUCHO
 Industrialdea Zona A - Pab. 35.
 Asteasu E-20159, Gipuzkoa
 Spain

Tel.: +34 843 74 00 13

sales@amcsa.es

www.mecanocaucho.com

Elastic properties



AMC MECANOCAUCHO
Industrialdea Zona A - Pab. 35.
Asteasu E-20159, Gipuzkoa
Spain

Tel.: +34 843 74 00 13

sales@amcsa.es

www.mecanocaucho.com

Technical characteristics

-

Rubber elastomer compound mixed with Barite.

-

MP5: 2.6mm / MP 10: 5mm

-

1230x1030 mm